

# EPOXIDIZED SOYBEAN OIL

GRADE	UNIT	TEST METHOD	◆ KANAMOLL 620	◆ KANAMOLL 650	◆● KANAMOLL 651
			ESBO 6.2	ESBO 6.5	ESBO 6.5 FG
PROPERTIES					
Appearance		Visual	Pale Yellow Clear Liquid		
Colour (Max.)	Hazen	ASTM D-1045-08	150	150	150
Specific Gravity at 27°C	N/A	ASTM D-1045-08	0.996 ± 0.003	0.996 ± 0.002	0.996 ± 0.002
Moisture Content (Max.)	% By Mass	ASTM E-203-08	0.10	0.10	0.10
Acid Value (Max.)	% By Mass	ASTM D-1045-08	1.0 ± 0.1	1.0 ± 0.1	1.0 ± 0.1
Ester Value	mg KOH/gm	ASTM D-1045-08	1.0 ± 0.2	1.0 ± 0.2	1.0 ± 0.2
Oxirane Value (Min.)		HBR Method	6.2 ± 0.1	6.5 ± 0.1	6.5 ± 0.1
Iodine Value (Max.)		Wij's Method	5	3	3
REACH Compliance	Y/N		Yes	Yes	Yes

◆ New Launch

● Food Contact Approved