

## **KANATOL - 3800**

**Chemical Nature** 

TRI OCTYL TRIMELLITATE (TOTM)

Primary plasticizer for PVC and PVC copolymers

Chemical Name :-

Molecular Formula :-

Molecular Weight :-Molecular Structure :-

Trade Name

Trimellitic anhydride acid ester of C<sub>8</sub>alcohol

1-

 $C_{33}H_{54}O_{6}$ 546.9

## Tri (2-Ethylhexyl) Trimellitate TOTM, TEHTM $C_{6}H_{3}(COOC_{8}H_{17})_{3}$

		H <sub>3</sub>			
	П Г -C-O-CH <sub>2</sub> -CH-CH -C-O-CH <sub>2</sub> -CH-CH -C-O-CH <sub>2</sub> -CH-CH U I O CH <sub>2</sub> -CH C-O-CH <sub>2</sub> -CH-CH <sub>2</sub> -CH <sub>2</sub> -CH O CH <sub>2</sub> -CH	I <sub>2</sub> -CH <sub>2</sub> -CH <sub>2</sub> -CH <sub>3</sub>			
	CAS Number :- UN. NO :-	3319-31-1			
	EINECS NO :-	222-020-0			
Specification	Characteristics	Unit	Test Method	Value	
	Colour Volatile Loss (130°C/3Hrs) Ester Value Acidity Moisture Specific Gravity (27°C) Ester content Heat Stability (180°C/2Hrs) Acidity after heat treatment Plasticizing Esters by GC Residual alcohol		ASTM-D-1045-86 KLJTM ASTM-D-1045-86 ASTM-D-1045-86 ASTM-D-1045-86 ASTM-D-1045-86 ISI-9591-96 ASTM-D-1045-86 KLJTM KLJTM	50 max. 0.10 max. 303-310 0.030 max. 0.10 max. 0.985–0.995. 99.00 min. 65. 0.05. 99.00 min. 0.10 max.	
	<b>Typical Properties</b>				
	Volume Resistivity Boiling Point @ 7 mbar Pour point Viscosity at 20°C Flash Point Refractive Index (27°C)	Ohmcm °C °C cp °C –	KLJTM lit. lit. KLJTM KLJTM ASTM-D-1045-86	5.0±1.0 X 10 <sup>11</sup> 283. - 46. 272-277. 250. 1.483–1.487.	
Total Solution in Plasticizers					

Contact: plasticizer@kljindia.com

An ISO 9001:2000 and ISO 14001:2004 conglomerate

www. kljindia.com



KLJ G Trust built on p			
KANATOL	- 3800		
Properties	<b>TOTM</b> is almost colourless and oily liquid, free of foreign materials <b>TOTM</b> is a primary branched monomeric plasticizers for vinylhomopolymer and Copolymer resins. <b>TOTM</b> is suggested for use in those end-use areas where Extreme low volatility is required.		
Application	<b>TOTM</b> provide desirable properties in vinyl applications which require good plasticizer / resin compatibility , low volatility , resistance to extraction by soapy water and good electrical properties.		
	<b>TOTM</b> is often a good substitute for polyester polymeric plasticizers where improvements in processing are desired.		
	<b>TOTM</b> is a specialty plasticizer that offers permanence, good extraction resistance, superior high temperature performance and excellent electrical properties.		
Plasticizing Efficiency	1.17		
Compatibility with Secondary Plasticizers	Very limited in comparision of DOP.		
Packing & Storage	<b>TOTM</b> is packed in 200/225 kg iron drum / HDPE drum, 20 - 22 MT in Flexi tank / ISO tank / road tanker. It is stored in tightly closed container, in a cool, dry & ventilated area.		
Shelf Life	Original characteristics remain intact for 24 months, if kept in recommended storage,		
Safety	The MSDS can be provided on request.		
Disclaimer	The data contained in this publication are based on our current knowledge and experience. During processing, there are so many factors which may affect the application part of <b>TOTM</b> , so these data neither imply any guarantee of certain properties, nor the suitability of the product for the specific purpose. Any data given in this publication may change without prior information and donot constitute the agreed quality of our product.		

**Total Solution in Plasticizers** 

Contact: plasticizer@kljindia.com

An ISO 9001:2000 and ISO 14001:2004 conglomerate

www. kljindia.com