



KLJ GROUP

XLPE COMPOUND



July 2020, Ed3

TECHNICAL INFORMATION

KLJ XL 01 HS FR

AMBIENT CURABLE FLAME RETARDANT SIOPLAS COMPOUND FOR INSULATION OF LOW VOLTAGE POWER CABLE

Description:

KLJ XL 01 HS/KLJ XL MB PT3 MD/KLJ XL FR MB 01 is a silane crosslink able natural compound as well as Flame retardant properties by improving the limiting Oxygen index. KLJ XL FR MB 01 is halogenated

This product consists of 3 components viz. Grafted polymer (KLJ XL 01 HS), Catalyst master batch (KLJ XL MB PT3 MD) and FR additive master batch (KLJ XL FR MB 01) for LT Power Cable application.

Application:

KLJ XL 01 HS/KLJ XL MB PT3 MD/KLJ XL FR MB 01 is designed for insulation of low voltage cable.

Specification:

KLJ XL 01 HS/KLJ XL MB PT3 MD/KLJ XL MB FR 01, in blend meets the applicable requirements as below when processed using sound extrusion and testing procedure:

IS 7098 Part I

IEC 60502 -1

The standards referred to above is a short selection of standards and does not cover all applicable standards. Contact your KLJ representative for additional information.

Special Features:

KLJ XL 01 HS/KLJ XL MB PT3 MD/KLJ XL MB FR 01 insulation system offers:

- Excellent processing properties
- Outstanding curing speed
- Excellent surface finish
- Free from heavy metal
- Consistent quality



KLJ GROUP

XLPE COMPOUND



July 2020, Ed3

Technical Characteristics:

A) KLJ XL 01 HS

Properties	Unit	Test Method	Specification	Typical Value
Physical Properties				
Density	gm/cm ³	ASTM D 792	0.910- 0.925	0.916
Melt Flow Index (190°C, 2.16 kg Load)	gm/10min	ASTM D 1238	0.5 – 2.5	1.0
Contamination (Visual)	No./kg	KLJ TM	<5	0

B) KLJ XL 01 HS/KLJ XL MB PT3 MD/KLJ XL MB FR 01

Test Procedure: After mixing in proportion of 60:5:35 and extruded into a tape of 1.2 mm thickness, the tape is immersed in water at 95°C for 3 hours. The testing is carried out after conditioning this tape for further 3 hrs at ambient conditions.

Properties	Unit	Test Method	Specification	Typical Value
Physical Properties				
Density (60:5:35)	gm/cm ³	ASTM D 792		1.04
Tensile Strength at Break	MPa	IS 10810 Part 7	≥ 12.5	21
Elongation at Break	%	IS 10810 Part 7	≥ 200	500
Hot set at 200°C				
Hot Elongation after 15 min	%	IS 10810 Part 30	≤ 175	60
Permanent Set after 5 min	%	IS 10810 Part 30	± 15	1.3
Oven ageing at 135°C, 168 hours				
Tensile Strength at Break	%	IS 10810 Part 11	± 25	-5
Elongation at Break	%	IS 10810 Part 11	± 25	-7
Shrinkage @ 130°C / 1 hours	mg/cm ²	IS 7098	≤ 4	1.4
Limiting Oxygen Index	%	ASTM D 2863	≥24	25
Flammability Test		UL 94	V-0	Pass

Electrical Properties

Volume Resistivity	Ohm-cm	ASTM D 257	≥ 10 ¹⁴	2.0 x 10 ¹⁶
Dissipation Factor @ 250 V/50 Hz, 25 °C	-	ASTM D 150	≤0.004	0.0001
Dielectric Constant @ 250 V/50 Hz, 25 °C	-	ASTM D 150	≤2.2	2.0
Dielectric withstand (1000 V/Sec. rise @+25 °C) KV/mm		ASTM D 149	≥ 22	32



KLJ GROUP

XLPE COMPOUND



July 2020, Ed3

Processing Guidelines:

It is recommended to pre-heat the Catalyst Master Batch and Colour Master Batch (if any) at 80°C in hot air oven in 4-6 cm layers for 2-4 hours. The Grafted Polymer should never be pre-heated.

The Grafted Polymer and Catalyst Master batch should be mixed at a ratio 60:5:35 at room temperature without shearing, just before consumption. For thin wires lower dosage can work & need to be set depending on the size. Mixing in large quantities should be avoided, since any leftover premix cannot be stored.

It is essential that extruder should not be kept idle when filled with KLJ XL-01 HS / KLJ XL MB PT3 MD/KLJ XL FR MB 01 premix. It should be kept running at a low RPM if it is needed to be stopped for any reason like changeover of size etc.

Typically the following process condition is used:

Zone 1	Zone 2	Zone 3	Zone 4	Zone 5	Head	Die
160±10°C	175±10°C	180±10°C	190±10°C	200±10°C	205±10°C	210±10°C

This system is designed for processing with both, Pressure or Tube-on tooling. The use of a gradient cooling bath will improve the cable insulation physical properties further.

Conductor preheating up to 100°C is recommended when producing cables with a conductor up to 16 mm² for good bonding and mechanical properties.

Ambient Cross Linking Data:

The above extruded product can be cross-linked by keeping in ambient condition. Results will vary under different ambient condition.

Relative Humidity %	Temperature °C	Thickness mm	Time to reach 100% Hot Elongation, days
50	23	0.7	3 – 4
50	23	1.0	6 – 7
50	23	1.2	8 – 9

The time period of curing may vary case to case depending on other variables viz. cross section of cable, thickness of insulation, humidity level(Min. 50 – 60%), exposure outdoor condition, sun light, reel size and temperature etc.

For an insulation thickness above 1.2 mm, the time needed for optimum cross-linking should be ascertained by small trial runs; bulk production should be taken up only after getting satisfactory results.



KLJ GROUP

XLPE COMPOUND



July 2020, Ed3

Storage:

- KLJ-XL-01HS can be stored for 180 from date of manufacturing, however it is suggested to use within 90 days from the date of receipt. Shelf life is subject to storage in original intact packing, in cool and dry place, away from sunlight and weathering, storage temperature not generally exceeding 35°C.
- Use the compound immediately, may be within 1 to 2 hours, of opening the bag.

Packaging:

KLJ XL 01 HS (base material)

Form: Granules.

Package: 25 kg aluminium multilayer bag and 550 kg Top & Bottom discharge Octabin with aluminium liner.

KLJ XL MB PT3 MD Catalyst Master batch.

Form: Granules.

Package: 25 kg aluminium multilayer bag and in smaller aluminium pouch, if required.

KLJ XL FR MB 01 FR Master batch.

Form: Granules.

Package: 25 kg aluminium multilayer bag and in smaller aluminium pouch, if required.

Safety:

This compound is not classified as dangerous preparation.

The products are supplied in the form of free-flowing granules of approx. 2-3 mm size and can be readily handled with commercially available equipment. Handling and transport of the products may generate some dust and fines, which constitute a potential hazard for dust explosion. All metal parts in the system should, therefore, be properly grounded. Properly designed equipment and good housekeeping will reduce the risk. Inhalation of any type of dust should be avoided as it may cause irritation of the respiratory system.

The product is intended for industrial use only. MSDS is available on request.

For technical service & further information and assistance:

KLJ POLYMERS & CHEMICALS LIMITED UNIT-II

Head Office:- KLJ HOUSE 63, Rama Marg, Najafgarh Road,
New Delhi – 110 015 (INDIA)

Tel: +91-11-41427429, 25459706-08

Fax: +91-11-25910215, 25459709

E-mail: cable@kljindia.com

Disclaimer: The data given above are for the guidelines purpose only. Above compound is suitable to run on different machines; however some adjustments may be required on individual machine. All properties are tested as per ASTM/IS/IEC standards. Any data may change without prior information. The customers are advised to check the quality, prior to commercial use. There is no guarantee and/or warrantee what so ever, after processing.